

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.



(19)

(11) Publication number:

57138774 A

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **56024095**(51) Intl. Cl.: **H01M 2/08**(22) Application date: **19.02.81**

(30) Priority:

(43) Date of application
publication: **27.08.82**(84) Designated contracting
states:(71) Applicant: **MATSUSHITA ELECTRIC IND CO
LTD**(72) Inventor: **EDA NOBUO
TOYOGUCHI YOSHINORI
YOSHIMOTO KEIKO
MORITA TERUYOSHI**

(74) Representative:

(54) BATTERY


(57) Abstract:


PURPOSE: To improve the preserving property of a battery, by forming a sealing layer with a solid paraffin layer and a photosetting resin layer provided outside, in a battery where a resin-sealing layer is used to hermetically seal a negative electrode made of light metal.

CONSTITUTION: In a battery case 1, there are a positive electrode 2 made of graphite fluoride etc, a separator 3 and a liquid-holding material 4 mainly impregnated with an organic electrolytic solution. In the same battery case 1, there is an insulated cylinder 7 which contains a lithium negative electrode 5 and a collector 6 thereof. The battery case 1 is hermetically sealed with an epoxide resin layer 11 to form an organic electrolyte battery. In this case, a sealing layer is composed of a solid paraffin layer 9 inside, further a photosetting resin layer 10 outside, and said epoxide resin layer 11. The photosetting resin layer 10 made of

denatured acrylate resin is poured onto the paraffin layer 9, and then forced to set by irradiation of ultraviolet-rays.

COPYRIGHT: (C)1982,JPO&Japio





The Delphion
Integrated
View

Other Views:
INPADOC

Title: **JP57138774A2: BATTERY**
 ► Want to see a more descriptive title highlighting what's new about this invention?

Country: **JP Japan**
 Kind: **A**

Inventor(s): **EDA NOBUO
 TOYOGUCHI YOSHINORI
 YOSHIMOTO KEIKO
 MORITA TERUYOSHI**

Applicant/Assignee: **MATSUSHITA ELECTRIC IND CO LTD**
 Inquire Regarding
 Licensing
News, Profiles, Stocks and More about this company

Issued/Filed Dates: **Aug. 27, 1982 / Feb. 19, 1981**

Application Number: **JP1981000024095**

IPC Class: **H01M 2/08; H01M 6/16;**

Priority Number(s): **Feb. 19, 1981 JP1981000024095**

Abstract: **Purpose:** To improve the preserving property of a battery, by forming a sealing layer with a solid paraffin layer and a photosetting resin layer provided outside, in a battery where a resin-sealing layer is used to hermetically seal a negative electrode made of light metal.

Constitution: In a battery case 1, there are a positive electrode 2 made of graphite fluoride etc, a separator 3 and a liquid-holding material 4 mainly impregnated with an organic electrolytic solution. In the same battery case 1, there is an insulated cylinder 7 which contains a lithium negative electrode 5 and a collector 6 thereof. The battery case 1 is hermetically sealed with an epoxide resin layer 11 to form an organic electrolyte battery. In this case, a sealing layer is composed of a solid paraffin layer 9 inside, further a photosetting resin layer 10 outside, and said epoxide resin layer 11. The photosetting resin layer 10 made of denatured acrylate resin is poured onto the paraffin layer 9, and then forced to set by irradiation of ultraviolet-rays.


COPYRIGHT: (C)1982,JPO&Japio

► See a clear and precise summary of the whole patent, in understandable terms.

Family: Show known family members

Other Abstract Info: **CHEMABS 097(26)225613E**

Foreign References: **No patents reference this one**



View
Image

1 page





Nominate this
for the Gallery...

[Subscribe](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [FAQ](#) | [Site Map](#) | [Help](#) | [Contact Us](#)

© 1997 - 2002 Delphion Inc.